

IN THE SPECIFICATION:

Please amend the specification as follows:

[0036] Exemplary binder compositions of the present invention were manufactured and found to work very well with calcium phosphate cements. The components are listed according to their various weight percentages in the following Table.

Composition	Example 1	Example 2	Example 3	Example 4	Example 5
2-Pyrrolidone	3	5	2	3	3
Liponics EG-1 TM	5	3.5	2	5	5
(Ethoxylated glycerol)					
1,5-Pentanediol	5.5	5	0	3.5	3.5
Phytic acid	3	0	0	3	3
Citric acid	2	2	0	0	0
Surfynol® 465	0.75	1	1	0.75	0.75
Tergitol® 15-S-5/7	1	1		1	1
H ₃ PO ₄	0	5	10	0	2
NH ₄ H ₂ PO ₄	0	0	10	0	0
Poly(vinyl phosphoric acid)	0	0	0	3	0
(MW < 20,000)					
Poly(acrylic acid)	0	0	0	0	3
(MW < 20,000)					
Magenta M377-Na	2	0		2	0
Direct Blue 199-Na	0	3		0	3
Direct Yellow 132-Na	0	0	3	0	0
Balanced water	77.75	74.5	72	78.75	75.75